

Listing of Claims

1. (Currently Amended) A hot dip coating apparatus for coating a steel strip wherein the strip is immersed in a bath of coating alloy containing aluminum, the apparatus comprising:
a bath of molten coating alloy containing Al-Zn alloy aluminum,
at least one component immersed in the bath of coating alloy containing Al-Zn alloy aluminum, the at least one component having a surface that comes into contact with the bath when in use,
wherein the at least one component is made from stainless steel containing greater than 0.10 wt % an appreciable amount of nitrogen distributed substantially uniformly throughout its microstructure as an austenite stabiliser.
2. (Cancelled)
3. (Previously Presented) The hot dip coating apparatus according to claim 1, wherein the at least one component is a sink roll under which the steel strip is passed.
4. (Currently Amended) The hot dip coating apparatus for coating a steel strip wherein the strip is immersed in a bath of coating alloy containing aluminum, the apparatus comprising:
a bath of molten coating alloy containing Al-Zn alloy aluminum,
at least one component immersed in the bath of coating alloy containing Al-Zn alloy aluminum, the at least one component having a surface that comes into contact with the bath when in use,
wherein the at least one component includes at least one layer made from stainless steel containing greater than 0.10 wt % an appreciable amount of nitrogen distributed uniformly through its microstructure as an austenite stabiliser.
5. (Cancelled)

6. (Previously Presented) The hot dip coating apparatus according to claim 4, wherein the at least one component includes a further layer, and wherein the stainless steel layer containing the nitrogen is disposed between the surface and the further layer.
7. (Previously Presented) The hot dip coating apparatus according to claim 6, wherein the further layer is formed from stainless steel.
8. (Cancelled)
9. (Cancelled)
10. (Cancelled)
11. (Currently Amended) The hot dip coating apparatus according to claim 4 [[2]], wherein the at least one component is a sink roll under which the metal strip is passed.
12. (Currently Amended) The hot dip coating apparatus according to claim 11 [[5]], wherein the at least one component includes a further layer, and wherein the stainless steel layer containing the nitrogen is disposed between the surface and the further layer.
13. (Cancelled)
14. (Cancelled)
15. (Cancelled)
16. (Cancelled)
17. (Cancelled)

18. (Currently Amended) A method of coating a steel strip wherein the strip is immersed in a bath of coating alloy containing Al-Zn alloy aluminum, the method comprising the steps of:

providing a bath of molten coating alloy containing Al-Zn alloy aluminum;

providing a component made from stainless steel containing greater than 0.10 wt % an appreciable amount of nitrogen distributed substantially uniformly through its microstructure as an austenite stabiliser;

immersing said component within the molten coating alloy; and

passing the steel strip about said component immersed in the bath.

19. (Cancelled)